

DIMENSIONAL DATA FOR STANDARD AND SCHEDULE PIPE

CARBON STEEL

SIZE		1/8	1/4	3/8	1/2	3/4	1	1 1/4	1 1/2	2	2 1/2	3	3 1/2	4	5	6	8	8	10	10	10	12	12	14	16	18	20	24	30
Standard	Outside Dia.	.405	.540	.675	.840	1.050	1.315	1.660	1.900	2.375	2.875	3.500	4.000	4.500	5.563	6.625	8.625	8.625	10.750	10.750	10.750	12.750	12.750	14.00	16.00	18.000	20.000	24.000	30.000
	Inside Dia.	0269	0364	0493	.600	.824	1.049	1.380	1.610	2.067	2.469	3.068	3.548	4.026	5.047	6.065	8.071	7.981	10.192	10.136	10.020	12.090	12.000	13.250	15.250	17.250	19.250	23.250	29.250
	Wall Thick.	.068	.088	.091	.109	.113	.133	.140	.145	.154	.203	.216	.226	.237	.258	.280	.277	.322	.279	.307	.365	.330	.375	.375	.375	.375	.375	.375	.375
	Wt. Per Ft. PE.	.24	.42	.57	.85	1.13	1.68	2.27	2.72	3.65	5.79	7.58	9.11	10.79	14.62	18.97	24.69	28.55	31.20	34.24	40.48	43.77	49.56	54.57	62.58	70.59	78.60	94.62	119.00
Extra Heavy	Inside Dia.	.215	.302	.423	.546	.742	.957	1.278	1.500	1.939	2.323	2.900	3.364	3.826	4.813	5.761	7.625		9.750			11.750		13.000	15.000	17.000	19.000	23.000	29.000
	Wall Thick.	.095	.119	.126	.147	.154	.179	.191	.200	.218	.276	.300	.318	.337	.375	.432	.500		.500			.500		.500	.500	.500	.500	.500	.500
	Wt. Per Ft. PE.	.31	.54	.74	1.09	1.47	2.17	3.00	3.63	5.02	7.66	10.25	12.51	14.98	20.78	28.57	43.39		54.74			65.42		72.09	82.77	93.45	104.13	125.49	157.53
Double Extra Heavy	Inside Dia.				.252	.434	.599	.896	1.100	1.503	1.771	2.300	2.728	3.152	4.063	4.897	6.875												
	Wall Thick.				.294	.308	.358	.382	.400	.436	.552	.600	.636	.674	.750	.864	.875												
	Wt. Per Ft. PE.				1.71	2.44	3.66	5.21	6.41	9.03	13.70	18.28	22.85	27.54	38.55	53.16	72.42												
Schedule 40	Inside Dia.	.269	.364	.493	.622	.824	1.049	1.380	1.610	2.067	2.469	3.068	3.548	4.026	5.047	6.065	7.981		10.020			11.938		*13.124	15.000	*16.876	18.814	22.626	
	Wall Thick.	*.068	*.088	*.091	*.109	*.113	*.133	*.140	*.145	*.154	*.203	*.216	*.226	*.237	*.258	*.280	*.322		*.365			.406		.438	♥.500	.562	.593	.687	
	Wt. Per Ft. PE.	.24	.42	.57	.85	1.13	1.68	2.27	2.72	3.65	5.79	7.58	9.11	10.79	14.62	18.97	28.55		40.48			53.53		63.37	82.77	104.15	122.91	171.17	
Schedule 80	Inside Dia.	.215	.266	.423	.546	.742	.957	1.278	1.500	1.939	2.323	2.900	3.364	3.826	4.813	5.761	7.625		9.564			11.376		12.500	14.314	*16.126	17.938	*21.564	
	Wall Thick.	♥.095	♥.119	♥.126	♥.147	♥.154	♥.179	♥.191	♥.200	♥.218	♥.276	♥.300	♥.318	♥.337	♥.375	♥.432	♥.500		.593			.687		.750	.843	.937	1.031	1.218	
	Wt. Per Ft. PE.	.31	.54	.74	1.09	1.47	2.17	3.00	3.63	5.02	7.66	10.25	12.51	14.98	20.78	28.57	43.39		64.33			88.51		106.13	136.46	170.75	208.87	296.36	
Schedule 160	Inside Dia.				.466	.614	.815	1.160	1.338	1.689	2.125	2.624		3.438	4.313	5.189	6.813		8.500			10.126		*11.188	*12.814	*14.438	*16.064	*19.314	
	Wall Thick.				.187	.218	.250	.250	.281	.343	.375	.438		.531	.625	.718	.906		1.125			1.312		1.406	1.593	1.781	1.968	2.343	
	Wt. Per Ft. PE.				1.30	1.94	2.84	3.76	4.86	7.44	10.01	14.32		22.51	32.96	45.30	74.69		115.65			160.27		189.12	245.11	308.51	379.01	541.94	

♥ Wall thickness identical with thickness of "Extra Heavy" pipe

* Although three sizes are listed as standard schedule numbers, they are not at present available from the seamless pipe mill

* Wall thickness identical with thickness of "Standard Weight" pipe

MSS, Inc. is not responsible for any printing errors in the data contained herein.
Although care was taken for proper representation, verification of all specifications
is the sole responsibility of the customer.